ARTIFICIAL TURF

# TEMPO

## Performance Training Turf

T E M P O
MOVEMENT
SPEED

- Lighter face weight and lower yarn density
- Reduced standing pile resistance
- Foam backing eliminating the need for additional shock pad
- Built for repeated multi-directional movements



### CONSTRUCTION

- Face system 19MM
- Primary backing
- 5mm Foam

### SPECIFICATIONS

| | |
|---|---|
| Pile height | 3/4 in. - 19MM |
| Fabric width | 15 ft |
| Color | 7 Options |
| Warranty | 8 Years |

### APPLICATIONS

- Sled Pushes
- Batting Cages
- Training Zones
- Speed & Agility Training



508-816-2604 sales@spsurfacing.com

# TEMPO COLORS / SPECS



## COLORS



Black | Blue | Green | Clay | Red | White | Grey

## FACE SYSTEM · 19MM

| | |
|---|---|
| Color | 7 Options |
| Yarn cross-section | Tape (slit-film) + nylon thatch |
| Secondary thatch yarn | Nylon, 5,200/8 |
| PE Yarn denier / ends | 8,040 / 1 |
| Total yarn linear density | 13,240 Denier |

## WEIGHT & CUSHION

| | |
|---|---|
| Face weight | 58 oz/yd² |
| Total fabric weight | 127 oz/yd² |
| Primary backing weight | 6 oz/yd² |
| Coating Type | 5mm Foam |
| Secondary coating weight | 63 oz/yd² |
| Pile height (nominal) | 3/4 in. - 19MM |

## PERFORMANCE & COMPLIANCE (ASTM)

| CRITERIA | TYPICAL RESULTS | TEST STANDARD |
|---|---|---|
| Tuft bind | >8lbs. | D-1335 |
| Grab tear strength (avg) | >200 lbs. | D-5034 |
| Yarn breaking strength | >19 lbs. | D-2256 |
| Elongation to break | >60% | D-2256 |
| Yarn melting point | 248°F | D-7138 |
| Lead content | <50 ppm | F-2765 |
| Flammability | Pass | D-2859 |
| Machine gauge | 3/16 in | D-5793 |
| Fabric width | 15 ft | — |
| Sustainability / Warranty | Recyclable / 8 years | — |

SPORT PRO SURFACING

CONTACT US

508-816-2604 sales@spsurfacing.com